



CANUCK
COMPOUNDERS
INC.

180 SHELDON DRIVE, CAMBRIDGE, ON CANADA N1R 6V1
TEL : 519 621 6521 FAX : 519 621 0320

BK 3-7-5

Automotive Grade Black Copolymer Polypropylene

GENERAL

Material Status	Commercial: Active
Availability	North America
Forms	Pellets

PHYSICAL

Property (Condition)	Value Unit	Method
Melt Flow Rate (230 °C / 2.16 kg)	17.0 g/10 min	ASTM D1238
Density	0.935 g/cm ³	ASTM D792

MECHANICAL

Property (Condition)	Value Unit	Method
Tensile Strength @ Yield (23 °C)	18 Mpa	ISO 527
Tensile Modulus (23 °C)	710 Mpa	ISO 527
Flexural Modulus (23 °C)	800 Mpa	ISO 178

THERMAL

Property (Condition)	Value Unit	Method
HDT @.455 Mpa	65°C	ISO 75

IMPACT

Property (Condition)	Value Unit	Method
Notched Izod Impact (23 °C)	25 kJ/m ²	ISO 180A
Gardner Impact (23°C)	600 in-lbs	ASTM D5420
Gardner Impact (-15°C)	560 in-lbs	ASTM D5420

Materials are tested at 23± 2°C and 50± 5% relative humidity unless otherwise noted.

RELATED TERMINOLOGY

Canuck manufactures a number of products with various terminologies and physical properties. The data above represents a basic Automotive Grade, Recycled Black Copolymer Polypropylene.

Property Notes

This data represents typical properties, and should not be construed as specifications.

The data above is typical of Black material only.

No information supplied by Canuck Compounders Inc. constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon Canuck Compounders Inc. or other customer experience. Canuck Compounders Inc. makes no warranties concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use.

