

180 SHELDON DRIVE, CAMBRIDGE, ON CANADA N1R 6V1 TEL: 519 621 6521 FAX: 519 621 0320

BK 8-8-4

GENERAL

Automotive Grade UV Stabilized Black Thermoplastic PolyOlefin (TPO)

GENERAL		
Material Status		Commercial: Active
Availability		North America
Forms		Pellets
PHYSICAL		
Property (Condition)	Value Unit	Method
Melt Flow Rate (230 °C / 2.16 kg)	10.0 g/10 min	ASTM D1238
Density	0.94 g/cm³	ASTM D792
Shrinkage	1.50%	ASTM D955
MECHANICAL		
Property (Condition)	Value Unit	Method
Tensile Strength @ Yield (23 °C)	15 Mpa	ISO 527
Tensile Elongation at break (%)	200%	ISO 527
Flexural Modulus (23 °C)	700 Mpa	ISO 178
THERMAL		
Property (Condition)	Value Unit	Method
HDT @ 0.455 Mpa	60°C	ISO 75
IMPACT		
Property (Condition)	Value Unit	Method
Notched Izod Impact (23 °C)	40 kJ/m²	ISO 180A
Gardner impact (-30 °C)	270 in-lb	ASTM D5420
Multiaxial Impact @ -30 °C	15 J	ASTM D3763
HARDNESS		
Property (Condition)	Value Unit	Method
Durometer Shore D	60	ASTM D2240

Materials are tested at $23\pm2^{\circ}$ C and $50\pm5\%$ relative humidity unless otherwise noted.

RELATED TERMINOLOGY

Canuck manufactures a number of products with various terminologies and physical properties. The data above represents a basic Automotive Grade, Recycled Black Thermoplastic PolyOlefin.

Property Notes

This data represents typical properties, and should not be construed as specifications.

The data above is typical of Black material only.

No information supplied by Canuck Compounders Inc. constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon Canuck Compounders Inc. or other customer experience. Canuck Compounders Inc. makes no warranties concerning the suitability of fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use.