



Canuck Compounders Inc.

Product Data Sheet

BK 8-8-7RUV Black, UV Stabilized TPO

GENERAL

Material Status	Commercial: Active
Availability	North America
Forms	Pellets

PHYSICAL

Property (Condition)	Value Unit	Method
Melt Flow Rate (230 °C / 2.16 kg)	32.0 g/10min	ASTM D1238
Filler Content	7.00%	ASTM D4218
Density	0.95g/cm ³	ASTM D792

MECHANICAL

Property (Condition)	Value Unit	Method
Tensile Strength @ Yield (23 °C)	18.0 Mpa	ISO 527
Flexural Modulus (23 °C)	1150 Mpa	ISO 178

IMPACT

Property (Condition)	Value Unit	Method
Notched Izod Impact (23 °C)	44 kJ/m ²	ISO 180A
Notched Izod Impact (-40 °C)	4.5 kJ/m ²	ISO 179A

RELATED TERMINOLOGY

Canuck manufactures a number of products with various terminologies and physical properties. The data above represents a basic Black, UV Stabilized Recycled TPO Compound.

Property Notes

This data represents typical properties, and should not be construed as specifications.

The data above is typical of Black material.

No information supplied by Canuck Compounders Inc. constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon Canuck Compounders Inc. or other customer experience. Canuck Compounders Inc. makes no warranties concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use.