



# Canuck Compounds Inc.

## Product Data Sheet

### 8-8-6MF20 Mineral Filled TPO

#### GENERAL

Material Status	Commercial: Active
Availability	North America
Forms	Pellets

#### PHYSICAL

Property (Condition)	Value Unit	Method
Melt Flow Rate (230 °C / 2.16 kg)	20.0 g/10 min	ASTM D1238
Density	1.04g/cm <sup>3</sup>	ASTM D792

#### MECHANICAL

Property (Condition)	Value Unit	Method
Tensile Strength @ Yield (23 °C)	19.0 Mpa	ISO 527
Flexural Modulus (23 °C)	1900 Mpa	ISO 178

#### IMPACT

Property (Condition)	Value Unit	Method
Notched Izod Impact (23 °C)	50 kJ/m <sup>2</sup>	ISO 180A
Notched Izod Impact (-30 °C)	8.0 kJ/m <sup>2</sup>	ISO 180A
Notched Charpy Impact (23 °C)	55 kJ/m <sup>2</sup>	ISO 179A
Notched Charpy Impact (-30 °C)	8.0 kJ/m <sup>2</sup>	ISO 179A
Gardiner Impact (-30 °C)	480 in/lb.	ASTM D5420

#### THERMAL

Heat Deflection Temperature (0.45 Mpa)	110°C	ISO 75
--	-------	--------

#### RELATED TERMINOLOGY

Canuck manufactures a number of products with various terminologies and physical properties. The data above represents a basic Black/Natural TPO Compound.

#### Property Notes

This data represents typical properties, and should not be construed as specifications.

The data above is typical of Black and Natural material.

No information supplied by Canuck Compounds Inc. constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon Canuck Compounds Inc. or other customer experience. Canuck Compounds Inc. makes no warranties concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use.